

10/583714

1

IAP20 RECEIVED 20 JUN 2006

AMENDMENT

(UNDER ARTICLE 11 OF THE LAW)

To: Commissioner of the Patent Office

1. International Application No. PCT/JP03/16814

2. Applicant

Name: Dainippon Ink and Chemicals, Inc.

Address: 35-58, Sakashita 3-chome, Itabashi-ku,  
Tokyo 174-8520 JAPAN

State of nationality: JAPAN

State of residence: JAPAN

3. Representative

Name: Patent Attorney (6490), SHIGA Masatake

Address: 2-3-1, Yaesu, Chuo-ku, Tokyo 104-8453 JAPAN

4. Item to be Amended: Claims

5. Contents of Amendment:

(1) Claims 11 to 14 are further added.

6. List of Attached Documents:

Replacement sheets of claims (page 21 of Japanese  
specification)

## (Amendment under PCT Article 34)

8. The laminated sheet according to claim 5, wherein the synthetic resin films for molding contain a thermoplastic resin, and a softening point of the binder resin of the decorative layer is lower than that of the thermoplastic resin.

9. The laminated sheet according to claim 5, which comprises an adhesive layer at the interface between the synthetic resin film for molding and the decorative layer.

10. The laminated sheet according to claim 5, wherein one or more synthetic resin films for molding provided on at least one side of the decorative layer are a transparent or translucent film, and a change rate of a surface luster value of the side of the transparent or translucent synthetic resin film for molding is 20% or less at 200% malleation.

11. (Added) The ink according to claim 1, which substantially contains no water.

12. (Added) The ink according to claim 1, wherein the metal thin film fragments are obtained from a metal thin film which

is obtained by at least one method selected from the group consisting of sputtering, malleation and aluminum vapor deposition.

13. (Added) The laminate sheet according to claim 5, which substantially contains no water.

14. (Added) The laminate sheet according to claim 5, wherein the content of the metal thin film fragments is from 10 to 60% by mass based on a non-volatile component in the ink, and the binder resin contains 50 to 500 mmol/kg of at least one selected from the group consisting of a carboxyl group, a phosphoric acid group, a sulfonic acid group, metal salts thereof and an amino group.